



AURELIA® DISTINCT

Premium Natural Latex Disposable Gloves

AURELIA® GLOVES

A SUPERMAX HEALTHCARE BRAND

sales@supermax.ie

+353 15256724

Units 1001 – 1012, Building
1000, Gateway Business Park,
New Mallow Road, Cork,
Ireland

aureliagloves.ie



Regulations	PPE Regulation (EU) 2016/425 Medical Device Regulation (EU) 2017/745, 93/42/EEC
Quality Standards	ISO 9001:2015 Quality Management Systems ISO 13485: 2016 Medical Devices Quality Management Systems
Harmonised Standards	BS EN ISO 374 - 1,2,4,5 Protective gloves against dangerous chemicals and microorganisms. BS EN 455 1-4 Medical gloves for single use. EN 420: 2003 + A1: 2009 Protective gloves. General requirements and test methods. BS EN 1186: 2002. Materials and articles in contact with foodstuffs.



XS	S	M	L	XL
29225	29226	29227	29228	29229

Sizes & Dimensions	Single wall thickness	Physical Properties												
<p>XS 70+10 mm S 80+10 mm M 95+10 mm L 110+10 mm XL > 110 mm</p> <p>min. 240 mm min. 240 mm min. 240 mm min. 240 mm min. 240 mm</p>	<p>① min. 0.15 mm ② min. 0.12 mm ③ min. 0.08 mm</p>	<table border="1"> <thead> <tr> <th></th> <th>Unaged</th> <th>Aged</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength</td> <td>Min. 18.0 MPa</td> <td>Min. 14.0 MPa</td> </tr> <tr> <td>Elongation</td> <td>Min. 650%</td> <td>Min. 500%</td> </tr> <tr> <td>Strength at Break</td> <td>Min. 6N</td> <td>Min. 6N</td> </tr> </tbody> </table>		Unaged	Aged	Tensile Strength	Min. 18.0 MPa	Min. 14.0 MPa	Elongation	Min. 650%	Min. 500%	Strength at Break	Min. 6N	Min. 6N
	Unaged	Aged												
Tensile Strength	Min. 18.0 MPa	Min. 14.0 MPa												
Elongation	Min. 650%	Min. 500%												
Strength at Break	Min. 6N	Min. 6N												



Latex



Powder Free



3 Years



HoneyComb



7.2g +/- 0.2g



White

